

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
23 September 2004 (23.09.2004)

PCT

(10) International Publication Number  
**WO 2004/080918 A1**

(51) International Patent Classification<sup>7</sup>: **C04B 41/87**

LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(21) International Application Number:  
PCT/CZ2003/000019

(22) International Filing Date: 13 March 2003 (13.03.2003)

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(25) Filing Language: English

(26) Publication Language: English

(71) Applicant and

(72) Inventor: **PROCHAZKA, Jan** [CZ/CZ]; 273 01 Kamenné Zehrovice 23, Czech Republic (CZ).

**Published:**

- with international search report
- with amended claims

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: MANUFACTURING OF PHOTOCATALYTIC, ANTIBACTERIAL, SELF-CLEANING AND OPTICALLY NON-INTERFERING SURFACES ON TILES AND GLAZED CERAMIC PRODUCTS

(57) Abstract: The principle of the deposition technique uses ultrafine crystals of ceramic oxides deposited relatively cold on melted or partially melted surfaces of ceramic tiles and other glazed ceramics, creating a spotty deposition without a significant change of optical properties of the surface. Because the desired nano-substance is deposited cold in a solid state form on the hot "sticky" surfaces and rapidly cooled down, deposited material is directly melted into the substrate surface, but its outer side remains unchanged. It allows creating a deposition with the desired parameters, for amplifying and extending the antibacterial protection in the dark, these surfaces may contain noble and heavy metals, deposited either dry as a part of the powder, or in a separate step, directly on the surface by wet deposition followed by drying and calcination.



**WO 2004/080918 A1**

# **MANUFACTURING OF PHOTOCATALYTIC, ANTIBACTERIAL, SELF-CLEANING AND OPTICALLY NON-INTERFERING SURFACES ON TILES AND GLAZED CERAMIC PRODUCTS.**

## **TECHNICAL FIELD**

The present invention is related to manufacturing of photocatalytic, antibacterial, self-cleaning and sanitizing surfaces on ceramic tiles and other ceramics. The technique is creating a thin spotty deposition of  $\text{TiO}_2$  and other active ceramic materials, or their mixtures consisting of ultrafine crystals on the surface of glazed ceramic products (further Deposition).

## **BACKGROUND OF THE INVENTION**

Considerable scientific and industrial effort has been spent on creating a photocatalytic, antibacterial, sanitizing and self-cleaning ceramic tiles, bath tubs, toilet dishes and other sanitary ceramic products, while the optical properties such as gloss, color and good mechanical properties of the product surface are preserved.

The hottest candidates able to carry the task are  $\text{TiO}_2$  and  $\text{ZnO}$  ceramic oxides, which often have to be nano-sized and doped to be fully functional in this application.

Several methods have been used to obtain a thin and transparent layer of a photocatalytic material such as nano anatase, a crystal form of  $\text{TiO}_2$  on ceramic surfaces. However, cost, environmental issues and major technical difficulties were always associated with the preparation. Mechanical and optical properties of layers made by these techniques were not always satisfactory.

CVD methods are often used because the anatase layer is tightly attached to the glass and ceramic surfaces. However, using of  $\text{TiCl}_4$ , organometallic and organic compounds represents certain ecological risks. Chemical Vapor Deposition also cannot be used at very high temperatures because phase unstable anatase would undergo rutile phase transformation. It may also chemically react with some substrates, containing cations from first and second group of periodic table.

Sol-gel methods have been used often to deposit thin, optically transparent films onto glass and ceramics by hydrolysis of Titanium organometallic compounds followed by calcination at 400-600°C. The films produced by this method show good transparency and photocatalytic characteristics, but do not have a very good *mechanical resistance* against moisture and abrasion. The layer consist of small anatase crystals sintered in a mesoporous structure and causes strong optical interference on the surface.

Flame and Plasma sprayed TiO<sub>2</sub> layers are accompanied by phase changes and minimally a partial conversion of anatase into rutile crystal phase. These layers have good mechanical and abrasion properties, but they cannot be optically transparent and primary particles grow significantly during this high temperature deposition, lowering photocatalytic activity and properties associated with it. Porosity of these layers is another issue affecting the product quality.

Some industrial products are based on calcination of anatase mixed into silica gel and other binders. Even when no chemical reaction of anatase and the binder occurs, the anatase particles get encapsulated in the binder and the layer does not function the same as the anatase crystal surface. Silica coating has been used by TiO<sub>2</sub> pigment producers to block fotocatalytic activity of TiO<sub>2</sub> particles for decades.

Sputtering methods are not suitable for low cost products and mass production of large quantities. The control of TiO<sub>2</sub> crystal form and the layer density is another challenging problem for sputtering methods.

Japanese company TOTO Ltd. possesses number of patents describing general principle of manufacturing of ceramic tiles and other products with "Hydrotect" layer finishing. In this patented technology nanosized anatase is mixed into SiO<sub>2</sub> colloidal suspension with other inorganic compounds, sprayed wet on the surface of an already glazed tile and calcined till the top layer is firmly joint to the tile glaze. TOTO patents claim that TiO<sub>2</sub> exist as TiO<sub>2</sub> even after the calcination step, however, the TiO<sub>2</sub> photocatalytic activity is likely eliminated by the silica environment.

Most attempts to put titanium dioxide in the anatase form directly in glazes to obtain photocatalytic surface failed because of chemical reaction during calcinations, encapsulation of the TiO<sub>2</sub> and other negative effects such as increasing the glaze melting point. Even if the high calcination temperature and presence of alkali metal ions does not

change chemical composition, it often converts anatase  $\text{TiO}_2$  form into rutile, or the particle size grows too big to be highly photocatalytic.

All technologies attempting to deposit phase unstable anatase crystal form on ceramic surfaces at high temperatures are facing difficulties such as particle size growth and phase transformation reducing photocatalytic activity and causing change in optical properties, or a chemical reaction eliminating completely the photocatalytic activity. A layer structures on the surface are either causing optical interference or the surface cannot have high gloss. Good adhesion of the top layer to the substrate surface may also be a problem.

Therefore, there is a need for an economical, large scale, high temperature process, which can make a strong deposition of ceramic compounds such as anatase in a desired crystal form, preferably with a high surface area, on the top of the substrate and directly exposed to the surface.

## **SUMMARY OF THE INVENTION**

The present invention provides an economical process for a production of surface treated ceramic products, with photocatalytic, antibacterial, self-cleaning and sanitizing features, without significant changes of the surface optical properties. The process is based on “cold” deposition of ultrafine ceramic powders, directly on melted and partially melted, ceramic surfaces. Many ceramic glazes are kinetic products, chemically reacting under the transformation temperature point, also providing good conditions (“sticky” surface) for nano-ceramic powder deposition described in this invention.

The deposition of aggregates, agglomerates, or micronized products of a significantly colder fine powder of ceramic compounds preferably occurs in the furnace heat zone, just before the cooling cycle, but it is not a limitation for most of the ceramics. The powder melts into the surface, undergoing partial sintering, creating a deposition, with desired chemical, optical, physical and mechanical properties after cleaning. The material, which is not bonded to the surface, is easy to remove after cooling. Removal of the excess of used material, leaving just the bottom layer, directly attached to the ceramic product surface, opens a clean surface of nanoparticles of deposited material. This thin

deposition usually does not significantly interfere with optical properties of the product, such as color or gloss, because it is a spotty deposition not a compact interferential layer. The deposition optimally makes shallow impacts less than  $1\mu\text{m}$  in size, which still does not reduce high gloss of the surface. The impact spot is covered by nanoparticles of anatase or other ceramic compound, which are too small to scatter light and change the look of the surface (Fig 5).

The size of the powder agglomerates or aggregates used in this process is preferably small. Optimal grain size of the agglomerated powder, consisting of small primary particles, is under  $100\mu\text{m}$ , and not much less than  $1\mu\text{m}$ .

The character of the deposition guaranties that the chemical composition of the surface is changed proportionally to the area, covered by the ceramic powder. One side of the powder particle is melted into the surface, while the outer side of the powder is always pure compound. This effect guarantees that the final layer is always the same as the powder side. The final layer of any spot hit by the powder has a chemical composition of the powder, and its crystal structure and morphology.

The nano-ceramic powder deposition on the melted ceramic surface of the substrate followed by rapid cooling reduces high temperature exposition of the powder to the minimum. It allows phase unstable anatase crystals to survive, reduce particle size growth and stop a chemical reaction in early stages.

The ceramics for the deposition can be photocatalytic and antibacterial compounds such as  $\text{TiO}_2$ -anatase and  $\text{ZnO}$ , heavy and noble metal doped nano-ceramic powders and mixtures thereof. Antibacterial agents such as silver can be deposited on the ceramic product surface either as a part of the powder or in an additional treatment of the surface followed by a calcination step.

**DESCRIPTION OF THE DRAWINGS:**

Fig 1. is a general flow sheet, showing the steps of one embodiment of the process of the present invention, where the powder deposition is provided by a nozzle system or in a “dust chamber”.

Step 1. is a container for storage of the cold feed powder material. Typically, spray dried agglomerates, aggregated materials or micronized products of nano anatase in pure or doped form are used. The agglomerates may contain antibacterial agents such as silver deposited on nano anatase surface also increasing anatase photocatalytic activity. Other doping increasing phase or thermal stability can also be used.

The feed powder is then sprayed through air or water cooled nozzles and the powder surrounded by “cold” air hit the surface of a melted or partially melted ceramic surface in the “dust chamber” (step 2). The substrate can have an irregular shape. As soon as the powder particles are melted into the glaze on the substrate surface, the surface is immediately cooled down to a safe temperature, to avoid particle size growth, phase change and a chemical reaction (step 3). Depending on the substrate and glaze used for the Deposition, sometimes several cooling steps may be required. Typically the first ramp down step is around 800°C. When a gentle cooling by a slow air draft, lowering the surface temperature is applied (step 8), it is quite easy to hold the surface temperature in the range, where no cracking, particle size growth or phase transformation occurs.

Thermal exposition of the powder particles should be as short as possible, for the same reasons. The hot powder is rapidly discharged and cooled in step 4. Materials used for the deposition modify the product surface, giving it special properties, which the material possesses itself, such as photocatalytic activity, antibacterial functioning, self cleaning properties, etc. In contrast to layers created on the surface by other techniques, the unique spotty deposition described in this invention does not have any significant optical interference effects and practically does not unintentionally change the optical quality of the product surface. Another aspect of this invention is that properties of the final ceramic surface are a combination of characteristics of the substrate and the deposited material and can be adjusted (Step 5). The deposited layer on the surface can go through simple cleaning, or it can be further modified. For example a wet deposition of Ag salt can be

dry on the surface and calcined (step6). Final product than is a photocatalytic and antibacterial tile or ceramic product, which can be selfcleaning and generally looks the same as the surface before deposition (step7).

Fig 2. Is a flow sheet of another embodiment of the process of the present invention, where the powder deposition created by discharging the substrate directly into cold powder of the ceramic compound.

Fig 3. Graphical description of the deposition from an optical and mechanical quality point of view.

- a) A deposition of nano anatase with bad properties-powder particles sunk too deep into the described layer, lost contact with the surface and worsened optical and mechanical properties of the surface.
- b) Good deposition resulting in good optical and mechanical properties of the final surface.
- c) Excellent shallow deposition . A surface with excellent optical and mechanical properties, after cleaning.

Fig 4. Describes the surface after the deposition and before and after cleaning.

- a) The surface after deposition-the ceramic compound powder particle is melted into the surface.
- b) The surface after removing anything that is not firmly attached to the surface, leaving a thin, spotty deposition of small primary crystals or their aggregates, which is changing the surface properties and chemical composition. After deposition the new ceramic is covering the surface up to 90%.
- c) Top section of the picture a) and b).

Fig 5. is a scanning electron microscope image of a ceramic tile, with a permanent deposition of about 40% of nano anatase on the surface.

Fig 6. is a scanning electron microscope image of a ceramic tile, with a permanent deposition of about 80% of nano anatase on the surface.

**The following examples illustrate, but do not limit, the present invention.**

#### **EXAMPLE I**

A layer of several types of commercial ceramic tiles was horizontally placed on a removable holder in a muffle furnace. The tiles all had glossy finish but different colors. The surface of each tile was cleaned with water and isopropanol before calcination. No exact transformation temperature and melting point of the glaze materials were known. The furnace temperature was set on 1100°C. It reached the temperature in about 90 minutes and was held for another 15 minutes. Then, the furnace was opened and within 5-10 seconds about 0.5g of nano-sized anatase in a form of fine, cold powder was blown into the furnace, using a simple pipe quartz nozzle. Air circulation of the powder was allowed for another minute, while the furnace was rapidly cooling down. Then the holder with the tiles was removed from the furnace and let cool down to the room temperature in an open air (Fig 1).

The tile surfaces were washed in DI water, dried and analyzed. None of the surfaces lost its gloss and except for one type of tile, they did not change the original appearance. The experiment with this type of tiles was repeated at 1020°C because in the previous experiment the glaze on the tile surface was obviously too thin during the 1100°C exposition and the powder agglomerates penetrated too deep into the glaze, affecting so the appearance of the surface (Fig3). Very similar results and hole free surface were obtained with the particular type of tiles after lowering the deposition temperature.

In other experiments, very fast air cooling was provided to the tiles, to make the nano-anatase exposition to the high temperature as short as possible to reduce possible particle size growth and phase transformation into rutile. Sometimes the cooling was bringing temperature of the tile surface under 500°C within seconds, but too fast cooling was often accompanied by tile cracking.



All the surfaces were strongly photocatalytic by the 1%AgNO<sub>3</sub> test. FE-SEM analysis indicated that total about 15-20% of the surface was directly covered by a thin nano anatase deposition. Generally, up to 90% of the glaze surface can be covered by this deposition technique, using micronized powders. High magnification imaging determined minimal changes in size of the nano crystals of anatase and their deposition directly on the top of the tile glaze. One side of the nanocrystals was melted into the glaze, the other side was exposed to the air. Mechanical properties of the treated surfaces did not change noticeably. When these treated surfaces were fresh, they showed superhydrophilic properties, which however rather quickly vanished. Two hour exposition to UV light brought the superhydrophilicity back.

## **EXAMPLE 2**

A set of the same commercial tiles as in the EXAMPLE 1 was ramped to 1050°C and then directly discharged into Ag-surface treated nano-anatase cold fine powder (Fig2). After washing and drying, high gloss surfaces were obtained (Fig3 and 4). Separate set of clean tiles treated as in the Example 1 was used for AgNO<sub>3</sub> surface post-treatment after anatase deposition. AgNO<sub>3</sub> solution (0.03%) was sprayed on the warm anatase treated tile surface, and calcined at 500°C after drying. Both experimental sets produced photocatalytic sanitizing surface.

## **EXAMPLE 3**

Several tiles of a commercial product Hydrotect were heated to 1100°C in a furnace. Then Ag surface treated nano anatase cold powder was deposited on the surface by a simple quartz nozzle air blow of the powder. The tiles on the surface were cooled during this deposition to about 800°C and then removed from the furnace. Antibacterial, photocatalytic tile surface was obtained, while most of the original properties of this product were preserved. The product did not change its look and still remained hydrophilic.

**EXAMPLE 4**

An irregular shape piece of a porcelain ceramic plate was slowly heated in the furnace to the point, when the surface became “sticky”. It was not clear, if the surface layer melted, or partially melted, as the ramping to 1200°C was taking place. Immediately after the temperature reached 1200°C, the furnace was opened and at temperature 1150°C a cold nano anatase powder was puffed on the surface by two “cold” air nozzles and the porcelain surface quickly but gently cooled in blowing air. A high gloss, photocatalytic surface was obtained.

**EXAMPLE 5**

A mixture of ZnO and anatase nanoparticles was deposited as cold powder by the technique described in EXAMPLE 1 at 1050°C on a ceramic tile. Before cleaning the surface, a diluted mixture (0.03%) of Ag and Cu nitrates was sprayed on the tile surface and calcined at 550°C. After cleaning this sanitary tile, a surface consisting of a spotty deposition of photocatalytic, self cleaning nano anatase and ZnO surrounded by a glaze with functional antibacterial surface was obtained.

**CLAIMS**

What is claimed is:

1. A novel process for manufacturing photocatalytic, antibacterial, selfcleaning and sanitizing surfaces on ceramic tiles and other ceramic products by solid state deposition.
2. A process using cold powders of nano-anatase and other ceramic photocatalytic and antibacterial compounds for deposition on a melted or partially melted surface of glazed ceramic tiles and other glazed ceramic products.
3. A process, where the ceramic material for the Deposition is a form of doped or undoped anatase, including nano sized anatase and thermally stable forms.
4. A process where the material for the Deposition is doped or undoped ZnO, including nano sized ZnO.
5. A process, where the substrate for Deposition is a glazed ceramic tile or another glazed ceramic product.
6. A process creating a spotty Deposition of a photocatalytic and/or antibacterial ceramic compound on the surface of the substrate, with a minimal negative impact on gloss and other optical properties of the product (optical interference free Deposition).
7. A process, where relatively cold solid phase powder is deposited on a hot substrate surface and cooled down fast enough to prevent chemical and physical changes of the deposited compound, such as changes in chemical composition, crystal phase and particle size.
8. A process, where the hot substrate surface is melted, partially melted or chemically reacting, having sticky properties and is able to bond the solid phase compound used for the Deposition.
9. A process, where up to 90% of the original substrate surface can be converted into a form of the deposited compound.

10. A process, where the deposited compound on the surface does not significantly change its own chemical composition, crystal phase and particle size.
11. All experiments described in the Examples and derivatives of these examples.
12. A process, where the properties of the surface after deposition described in this invention are a combination of characteristics of the surface layer used for deposition and the deposited compound.
13. A process, where silver, copper, heavy and noble metals possessing antibacterial characteristics and increasing PCA can be introduced either as a part of the dry powder Deposition, or is a separate step, using wet deposition, followed by drying and calcinations, creating additional antibacterial protection.
14. A process, where the deposition is made by shallow impacts of aggregated, agglomerated or micronized powders onto melted or partially melted surfaces and the solid particles melt into this surface on the substrate side, while the chemical composition and crystal phase of the other particle side does not change.

**AMENDED CLAIMS**

[received by the International Bureau on 08 January 2004 (08.01.04);  
original claims 1-14 replaced by amended claims 1-17 (2 pages).]


**CLAIMS**

What is claimed is:

1. A novel process for manufacturing of photocatalytic, antibacterial, self-cleaning and sanitizing surfaces on ceramic tiles and other ceramic products comprising:
  - a) creating a sticky surface on ceramic tiles or glazed ceramic products by heating;
  - b) depositing an active photocatalytic and antibacterial ceramic compound in a powder form on the sticky surface;
  - c) exposing and bonding the powder to the sticky surface;
  - d) rapidly cooling the surface with the powder deposition to temperatures under 850°C;
  - e) cooling the product to the room temperature.
2. A process of claim 1, further comprising removing the unbonded powder from the glazed surface.
3. A process of claim 1, wherein the powder of the active ceramic compound is selected from a group of photocatalytic and antibacterial compounds consisting of metal oxides.
4. A process of claim 3, wherein the metal oxide is TiO<sub>2</sub>, ZnO, CuO, Ag<sub>2</sub>O, SnO<sub>2</sub> and mixtures thereof.
5. A process of claim 4, wherein the powder of the active ceramic compound is TiO<sub>2</sub> crystal form of undoped or doped anatase, with the average particle size smaller than 100nm.
6. A process of claim 4, wherein the powder for Deposition is doped or undoped TiO<sub>2</sub> crystal form of rutile with the average particle size smaller than 500nm.
7. A process of claim 4, wherein the powder for Deposition is doped or undoped ZnO, with the average particle size smaller than 1 µm.
8. A process of claim 1b), wherein the powder is colder than the sticky surface.


9. A process of claim 1a), 1b) and 1c) wherein the sticky surface for powder deposition is melted, partially melted or chemically reacting and it is able to bond the solid phase ceramic compound used for the Deposition.
10. A process of claim 1d), wherein cooling is fast enough to prevent chemical and physical changes of the chemical composition, crystal phase and particle size of the deposited compound.
11. A process of claim 1, wherein the spotty deposition of the powder of the active ceramic compound covers up to 90% of the glazed surface.
12. A process of claim 10, wherein gloss and other optical properties of the product are not significantly changed by the Deposition.
13. A process of claim 1, wherein the excess of the powder of the active compound does not significantly change its own chemical composition, crystal phase, morphology and particle size during the Deposition and can be recycled.
14. A process of claim 1 further comprising doping the surface with heavy and noble metals possessing antibacterial character and extending the antibacterial properties of the product.
15. A process of claim 14, wherein the metals are selected from the group consisting of silver, copper, zinc and platinum.
16. A process of claim 14, wherein the metals are introduced as a part of the dry powder described in claim 1.
17. A process of claim 14 comprising doping the surface with noble and heavy metals by depositing water soluble salts on the surface received in claim 1e), followed by drying and short calcination at a temperature between about 300°C and about 900°C.

1/5




2/5

Fig 2.






3/5

**Fig 3.**


4/5

Fig 4.

a)





b)




c) Before surface cleaning after deposition.

After surface cleaning after deposition.




5/5

**Fig 5.**



**Fig 6.**



## INTERNATIONAL SEARCH REPORT

International Application No.

PCT/JP 03/00019

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C04B41/87

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C04B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, COMPENDEX

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 100 18 458 A (ERLUS BAUSTOFFWERKE) 18 October 2001 (2001-10-18) claims ---	1-14
A	DE 199 47 524 A (ERLUS BAUSTOFFWERKE) 1 February 2001 (2001-02-01) claims ---	1-14
A	PATENT ABSTRACTS OF JAPAN vol. 1999, no. 05, 31 May 1999 (1999-05-31) & JP 11 028784 A (TOTO LTD), 2 February 1999 (1999-02-02) abstract --- -/--	1-14

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## ° Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search

20 October 2003

Date of mailing of the international search report

28/10/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Rosenberger, J

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/CZ 03/00019

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>PATENT ABSTRACTS OF JAPAN  vol. 1996, no. 11,  29 November 1996 (1996-11-29)  &amp; JP 08 175887 A (TOTO LTD),  9 July 1996 (1996-07-09)  abstract  -----</p>	1-14

# INTERNATIONAL SEARCH REPORT

International application No.  
PCT/CZ 03/00019

## Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:  
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☒ Claims Nos.: 1-14 (in part)  
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:  
see FURTHER INFORMATION sheet PCT/ISA/210
3. ☐ Claims Nos.:  
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

## Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

### Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

Continuation of Box I.2

Claims Nos.: 1-14 (in part)

Present claims 1-14. relate to an extremely large number of possible methods. Support within the meaning of Article 6 PCT and disclosure within the meaning of Article 5 PCT is to be found, however, for only a very small proportion of the methods claimed. In the present case, the claims so lack support, and the application so lacks disclosure, that a meaningful search over the whole of the claimed scope is impossible. Consequently, the search has been carried out for those parts of the claim 1, which appear to be supported and disclosed, namely those parts relating to a process for manufacturing photocatalytic, antibacterial, selfcleaning and/or sanitising surfaces on ceramic tiles or other ceramic products by solid state deposition, wherein ultrafine ceramic powders are cold deposited directly onto melted or partially melted ceramic surfaces. Claims 2-14 were searched only insofar as they are limited to processes according to claim 1, i.e. as dependent from claim 1.

The applicant's attention is drawn to the fact that claims, or parts of claims, relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure.

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PC17/CZ 03/00019

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
DE 10018458	A	18-10-2001	DE WO	10018458 A1 0179141 A1	18-10-2001 25-10-2001
DE 19947524	A	01-02-2001	DE AT CZ DE DK EP	19947524 A1 235442 T 20002725 A3 50001530 D1 1072572 T3 1072572 A1	01-02-2001 15-04-2003 16-01-2002 30-04-2003 14-07-2003 31-01-2001
JP 11028784	A	02-02-1999	JP	3063735 B2	12-07-2000
JP 08175887	A	09-07-1996	NONE		